


COTTO

CEMENT 7.0









WHITE
MATT



GREY
MATT



SMOKE
MATT





ASH
MATT




ANTHRACITE
MATT




SIZES




R9



60x60
24"x24"



30x60
12"x24"



30x30
12"x12"

FINISH
MATT

COLORS
WHITE
GREY
ASH
SMOKE
ANTHRACITE

DECORS



HEXAGON
30x30 - 12"x12"



DIAMOND
30x30 - 12"x12"




CUBE
30x30 - 12"x12"




SLIM HEXAGON
30x30 - 12"x12"



STRIPS
30x60 - 12"x24"



STONE MOSAIC
30x60 - 12"x24"



ZIG ZAG
30x60 - 12"x24"



STONE STRIPS
30x60 - 12"x24"

TECHNICAL CHARACTERISTICS

		TECHNICAL FEATURES	SPECIFICATION	VALUE REQUIRED	*SPACE VALUES
REGULARITY CHARACTERISTICS		LENGTH AND WIDTH	ISO 10545-2	± 0.6%	+0.01%~+0.03%
		THICKNESS	ISO 10545-2	± 5.0%	+0.27%~+0.92%
		SQUARENESS	ISO 10545-2	± 0.5%	-0.05%~+0.02%
		STRAIGHTNESS OF THE EDGES	ISO 10545-2	± 0.5%	± 0.02%
		FLATNESS	ISO 10545-2	± 0.5%	+0.06%~+0.09%
STRUCTURAL CHARACTERISTICS		WATER ABSORPTION	ISO 10545-3	≤ 0.5%	0.43%
		BREAKING STRENGTH	ISO 10545-4	≥ 1300 N	2262N
MODULUS OF RUPTURE		≥ 35 N/mm ²		38.3 N/mm ²	
CHEMICAL CHARACTERISTICS		CHEMICAL RESISTANCE	ISO 10545-13	TEST METHOD AVAILABLE DECLARED VALUE	GA
		RESISTANCE TO STAINING	ISO 10545-14	TEST METHOD AVAILABLE DECLARED VALUE	PASSED
SAFETY CHARACTERISTICS		SLIP RESISTANCE INCLINED PLATFORM	DIN 51130	TEST METHOD AVAILABLE	R9
			DIN 51097		

SIZE, WEIGHT AND PACKAGING

SIZE	PIECES/BOX	MQ/BOX	KG/BOX	MQ/PALLET	KG/PALLET	BOX/PALLET
60x60	4	1.44	32	57.6	1305	40
30x60	8	1.44	32	57.6	1305	40
30x30	11	0.99	22	53.46	1213	54

FORMATS

	60x60	30x60	30x30
WHITE			
GREY			
ASH			
SMOKE			
ANTHRACITE			

MATT

THICKNESS



RECTIFIED



PLEASE PASTE YOUR NAMECARD HERE