


# BAVARIA

STONE 3. 0



space  
Ceramics + Porcelain





**NATURAL**  
MATT



R9



**SAND**  
MATT



R9



**BROWN**  
MATT



R9



**ANTHRACITE**  
MATT



**CHARCOAL**  
MATT






### SIZES



R9



60x60  
24"x24"



30x60  
12"x24"



30x30  
12"x12"

**FINISH**  
MATT

**COLORS**  
NATURAL  
SAND  
BROWN  
ANTHRACITE  
CHARCOAL

### DECORS



**HEXAGON**  
30x30 - 12"x12"



**DIAMOND**  
30x30 - 12"x12"



**CUBE**  
30x30 - 12"x12"



**SLIM HEXAGON**  
30x30 - 12"x12"



**STRIPS**  
30x60 - 12"x24"



**STONE MOSAIC**  
30x60 - 12"x24"













**ZIG ZAG**  
30x60 - 12"x24"





**STONE STRIPS**  
30x60 - 12"x24"

## TECHNICAL CHARACTERISTICS

		TECHNICAL FEATURES	SPECIFICATION	VALUE REQUIRED	*SPACE VALUES
REGULARITY CHARACTERISTICS		LENGTH AND WIDTH	ISO 10545-2	± 0.6%	± 0.03%
		THICKNESS	ISO 10545-2	± 5.0%	-3%
		SQUARENESS	ISO 10545-2	± 0.6%	0.04%
		STRAIGHTNESS OF THE EDGES	ISO 10545-2	± 0.5%	0.01%
		FLATNESS	ISO 10545-2	± 0.5%	0.08%
STRUCTURAL CHARACTERISTICS		WATER ABSORPTION	ISO 10545-3	≤ 0.5%	0.06%
		BREAKING STRENGTH	ISO 10545-4	≥ 1300 N	2489 N
		MODULUS OF RUPTURE		≥ 35 N/mm <sup>2</sup>	50.6 N/mm <sup>2</sup>
CHEMICAL CHARACTERISTICS		CHEMICAL RESISTANCE	ISO 10545-13	TEST METHOD AVAILABLE DECLARED VALUE	GA
		RESISTANCE TO STAINING	ISO 10545-14	TEST METHOD AVAILABLE DECLARED VALUE	PASSED
SAFETY CHARACTERISTICS		SLIP RESISTANCE INCLINED PLATFORM	DIN 51130	TEST METHOD AVAILABLE	R9
			DIN 51097		

## SIZE, WEIGHT AND PACKAGING

						
SIZE	PIECES/BOX	MQ/BOX	KG/BOX	MQ/PALLET	KG/PALLET	BOX/PALLET
60x60	4	1.44	32	57.6	1305	40
30x60	8	1.44	32	57.6	1305	40
30x30	11	0.99	22	53.46	1213	54

## FORMATS

	60x60	30x60	30x30
NATURAL	◇	◇	◇
SAND	◇	◇	◇
BROWN	◇	◇	◇
ANTHRACITE	◇	◇	◇
CHARCOAL	◇	◇	◇

◇ MATT

THICKNESS



RECTIFIED



PLEASE PASTE YOUR NAMECARD HERE