

OHIO

WOOD 2. 0



space
Ceramics + Porcelain





BEIGE

MATT



R9



GREY

MATT



R9



SAND

MATT



R9



BROWN

MATT  R9




TAUPE

MATT  R9



SIZES



15x90
6"x36"

DECORS



MOSAICS
30x30 - 12"x12"



R9

FINISH
MATT

COLORS
BEIGE
GREY
SAND
BROWN
TAUPE



STRIPS
30x60 - 12"x24"

TECHNICAL CHARACTERISTICS

| | | TECHNICAL FEATURES | SPECIFICATION | VALUE REQUIRED | *SPACE VALUES |
|----------------------------|--|-----------------------------------|---------------|---|---------------|
| REGULARITY CHARACTERISTICS | | LENGTH AND WIDTH | ISO 10545-2 | ± 0.6% | ± 0.03% |
| | | THICKNESS | ISO 10545-2 | ± 5.0% | -3% |
| | | SQUARENESS | ISO 10545-2 | ± 0.6% | 0.04% |
| | | STRAIGHTNESS OF THE EDGES | ISO 10545-2 | ± 0.5% | 0.01% |
| | | FLATNESS | ISO 10545-2 | ± 0.5% | 0.08% |
| STRUCTURAL CHARACTERISTICS | | WATER ABSORPTION | ISO 10545-3 | ≤ 0.5% | 0.06% |
| | | BREAKING STRENGTH | ISO 10545-4 | ≥ 1300 N | 2489 N |
| MODULUS OF RUPTURE | | ≥ 35 N/mm ² | | 50.6 N/mm ² | |
| CHEMICAL CHARACTERISTICS | | CHEMICAL RESISTANCE | ISO 10545-13 | TEST METHOD AVAILABLE DECLARED VALUE | GA |
| | | RESISTANCE TO STAINING | ISO 10545-14 | TEST METHOD AVAILABLE DECLARED VALUE | PASSED |
| SAFETY CHARACTERISTICS | | SLIP RESISTANCE INCLINED PLATFORM | DIN 51130 | TEST METHOD AVAILABLE | R9 |
| | | | DIN 51097 | | |

SIZE, WEIGHT AND PACKAGING

| SIZE | PIECES/BOX | MQ/BOX | KG/BOX | MQ/PALLET | KG/PALLET | BOX/PALLET |
|-------|------------|--------|--------|-----------|-----------|------------|
| 15x90 | 6 | 0.81 | 19 | 45.36 | 1089 | 56 |

FORMATS

15x90

| | |
|-------|---|
| BEIGE | ◆ |
| GREY | ◆ |
| SAND | ◆ |
| BROWN | ◆ |
| TAUPE | ◆ |

◆ MATT

THICKNESS



RECTIFIED



PLEASE PASTE YOUR NAMECARD HERE